



# BluCem HB30

## LIGHT WEIGHT HIGH BUILD MORTAR



BluCem HB30 is a one component cement powder which requires only the addition of water to form a concrete repair cementitious mortar.

BluCem HB30 is a trowellable, easy to apply product suitable for civil engineering applications. BluCem HB30 incorporates light weight fillers and advanced polymer additives to form a cementitious mortar which is low in permeability, dual shrinkage compensating and suitable for architectural finishing.

### Application Advantages

- Light weight
- High build
- Easy finishing and long pot life

### Lifecycle Advantages

- High durability
- Dual shrinkage compensation
- Superb architectural finishing

### About the Product

BluCem HB30 has excellent finishing properties through its use of special polymers and light weight fillers. This allows a long pot-life and malleable consistency of the mortar which ensures that the final finish is accurate and matching existing surfaces. BluCem HB30 is the benchmark for architectural repair mortars and first choice for architectural and heritage repair professionals because of its ease of use and excellent workability.

### Application Solutions

- Concrete protection
- Architectural repairs
- Floor repair and topping
- She-bolt hole repair

### Project Specification Clause

LIGHT WEIGHT HIGH BUILD MORTAR - The concrete repair cementitious mortar used for this project shall be a one component cement powder which requires only the addition of water to form a durable concrete repair product. It shall be a pre-blended product that has independent testing to validate the performance outlined in the technical data table on the following pages. BluCem HB30 manufactured by Blueey Technologies or equivalent shall be accepted.

### Project Examples

Bridge repair, building repairs, concrete structures, retail outlets, retaining walls, tunnel lining.





# BluCem HB30

## LIGHT WEIGHT HIGH BUILD MORTAR

### Application Specification

#### CONCRETE PREPARATION

- 1.1 All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications.
- 1.2 Host concrete must be roughened and aggregate exposed to ensure good bond. Removal of laitance is important to ensuring good bond. Shot-blasting, scarification, mechanical chipping or high pressure water blasting may be used to achieve a recommended minimum CSP3 surface finish. It is important to select a preparation method which is considerate to the application environment, host concrete, and surface finish requirements. The correct balance between roughening the surface and not causing further micro-cracking and damage should be trialed and assessed using adhesion test methods following initial preparation trials.
- 1.3 All surfaces must be free of dust, oils and surface contaminants. This may require steam cleaning or high pressure water blasting.
- 1.4 A perimeter edge of at least 10mm depth must be provided around the area for application.
- 1.5 Priming using BluCem API0 is recommended. Priming by saturation of the surface using water prior to application is also acceptable. Priming with epoxy primers or other products which prevent vapour transmission is not recommended.

#### STEEL PREPARATION

- 2.1 Following removal of all defective concrete, any partially exposed reinforcing bars shall be fully exposed to a depth of 20mm behind the bar.
- 2.2 If the bar has lost more than 20% of its original diameter then it should be replaced and the Structural Engineer must be consulted.
- 2.3 Where the original reinforcement is retained it must be cleaned to a standard surface purity of Sa 2.5 for chloride contaminated concrete and Sa 2.0 for carbonated concrete. This is best achieved by wet blasting or abrasive blasting.
- 2.4 If chloride contamination is present then high pressure wet blasting is the only acceptable method of cleaning. Priming of reinforcement is generally not required.
- 2.5 If the steel will be exposed to the atmosphere for several days after cleaning then an acceptable form of priming would be to mix BluCem HB30 into a slurry using BluCem API0 and apply a cement rich coating to the steel surface.

#### MIXING

- 3.1 Add BluCem HB30 to potable water in a clean vessel using a high shear mechanical mixer for at least three minutes. Do not mix more material than can be placed in 15 minutes. Add enough water to achieve the desired consistency within the water ratio limits specified in this data sheet.

#### APPLICATION

- 4.1 Work small amounts of mixed BluCem HB30 into the primed or dampened surface. Do not exceed 40mm of thickness in any wet layer.
- 4.2 Roughen the surface between each layer and wait until initial set or all latent heat has dissolved prior to application of next layer.

#### CURING

- 5.1 It is recommended that the final surface finish layer is coated with curing compound or otherwise maintained wet for at least three days.



# BluCem HB30

## LIGHT WEIGHT HIGH BUILD MORTAR

### Product Data

Please refer to Important Notice on following page

Packaging	20kg bags
Water Addition	3.2 - 3.4 litres per 20kg bag
Yield	16.0 litres per 20kg @ 3.2 litres water
Application Thickness	Refer to Bluey Technologies for advice and approval on pour thicknesses with dimensions exceeding 100mm
Maximum Particle Size	0.3mm

TESTED CHARACTERISTIC	STANDARD	RESULT
Portland Cement	AS3972	Complies
Aggregates	AS2758.0	Complies
Compressive Strength	AS1012.9	3.2 - 3.4 litres water per 20kg Trowellable 10MPa @ 24 hours 23MPa @ 7 days 27MPa @ 28 days
Coefficient of Thermal Expansion	EN 13295	14 $\mu$ strain/ $^{\circ}$ C
Chloride Ion Content	AS1012.20	<0.01%
Elastic Modulus	AS1012.17	3.2 - 3.4 litres water per 20kg Trowellable 10GPa
Tensile Strength	AS1012.10	3.2 - 3.4 litres water per 20kg Trowellable 2MPa
Drying Shrinkage	AS2350.13	850 $\mu$ strain @ 28 days
Electrical Resistivity	Taywood-Warner 4 Probe	20000ohm-cm @ 28 days
Flexural Strength	ASTM C348	4.5MPa @ 28 days
Setting Time	AS1012.18	Initial set - 300 minutes Final set - 420 minutes
Fresh Wet Density	AS1012.18	1560kg/m <sup>3</sup>



# BluCem HB30

## LIGHT WEIGHT HIGH BUILD MORTAR

### Contact Bluey

#### BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd  
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia  
Ph +61 7 3399 3635 Fax +61 7 3899 9822 [brisbane@bluey.com.au](mailto:brisbane@bluey.com.au)

#### SYDNEY

Bluey Technologies Pty Ltd  
Unit 3, 35 Higginbotham Road, Gladesville NSW 2111 Australia  
Ph +61 2 9807 2207 [sydney@bluey.com.au](mailto:sydney@bluey.com.au)

#### MELBOURNE

Bluey Technologies Pty Ltd  
PO Box 170, Tullamarine VIC 3043 Australia  
Ph +61 3 9826 5570 [melbourne@bluey.com.au](mailto:melbourne@bluey.com.au)

#### PERTH

Bluey Technologies Pty Ltd  
Ph +61 402 372 308 [perth@bluey.com.au](mailto:perth@bluey.com.au)

#### AUCKLAND

Bluey Technologies  
Ph +64 21 102 4797 [nz@bluey.com.au](mailto:nz@bluey.com.au)

[www.bluey.com.au](http://www.bluey.com.au)

#### BLUEY ASIA PACIFIC DISTRIBUTOR

##### QUICSEAL CONSTRUCTION CHEMICALS PTE LTD

No.7 Eunos Avenue 8A, Eunos Industrial Estate, (S)409460 Singapore  
Ph +65 6742 4466 Fax +65 6741 4666  
[www.quicseal.com](http://www.quicseal.com)

#### IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd