



BluCem SL50

RAPID FLOOR SELF-LEVELLING CEMENTITIOUS GROUT



BluCem SL50 is a one component cementitious powder which requires only the addition of water to form a self-levelling cementitious grout.

BluCem SL50 has been designed as a level finishing, non segregating, feathered edge finish product suitable for civil engineering applications. BluCem SL50 incorporates advanced superplasticisers and polymers to form a C Class dual shrinkage control, high strength, very high bond, scratch resistant and durable cementitious grout.

Application Advantages

- Easy to apply
- Self healing
- Level finishing
- Non segregating
- Feathered edge finish

Lifecycle Advantages

- Type C Class, dual shrinkage control
- High strength
- Very high bond
- Scratch resistant
- Durable
- Outdoor and indoor use

About the Product

BluCem SL50 is an extremely hard wearing, early strength, self-levelling grout manufactured from specially selected cements, aggregates and additives. This allows the product to be used in hard wearing applications and ensures a durable and long lasting installation. BluCem SL50 is a leader in its class of floor topping materials with its exceptionally high scratch resistance, strength and bond. It is the reliable choice for all challenging floor topping and repair applications.

Application Solutions

- Concrete repair
- Re-levelling finished concrete
- Repair of rain damaged concrete
- Floor repair and topping
- Joint repairs
- Underlays

Project Specification Clause

RAPID FLOOR SELF-LEVELLING CEMENTITIOUS GROUT - The self-levelling cementitious grout used for this project shall be a one component cementitious powder which requires only the addition of water to form a durable self-levelling product. It shall be a pre-blended product that has independent testing to validate the performance outlined in the technical data table on the following pages. BluCem SL50 manufactured by Blueey Technologies or equivalent shall be accepted.

Project Examples

Airport construction, bridge repair, building repairs, factory floors, car park decks, jetty construction and repair, concrete structures, retail outlets, road repairs, runway repairs and shutdowns, warehouse floors.





BluCem SL50

RAPID FLOOR SELF-LEVELLING CEMENTITIOUS GROUT

Application Specification

CONCRETE PREPARATION

- 1.1 All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications.
- 1.2 Host concrete must be roughened and aggregate exposed to ensure good bond. High pressure water blasting, mechanical chipping or shot blasting of the surface is recommended for this purpose.
- 1.3 All surfaces must be free of dust, oils and surface contaminants. This will require steam cleaning or high pressure water blasting if site conditions permit.
- 1.4 Priming using BluCem API0 primer is recommended. Application of BluCem SL50 must commence within 4 hours of primer application

MIXING

- 2.1 Measure and place 80% of the specified volume of potable water to the high shear mixing vessel. Start mixer and slowly add BluCem SL50 powder. If powder addition is too fast then large lumps will form and final mix will be slow reaching uniform consistency. Following addition of all powder, mix for 1 - 2 minutes or until uniform consistency then add final 20% of potable water. More or less water may be added within the ratio limits specified on this data sheet. Do not mix more material than can be placed in 10 minutes.

PUMPING

- 3.1 Once the grout has been mixed you need an effective pumping method to deliver it to the area of application. Various models of batch mixers and continuous mixers are available for use, all with varying specifications. It is important to match your application's specifics with the capabilities of the mixer and pump. Bluey Technologies are able to recommend the right mixer for your project.
- 3.2 Prior to pumping grout, rinse the mixer and charge the pump hopper with sufficient water to flush and cool the pump and all grout lines thoroughly. Check to ensure that all lines and hoses are clear and unobstructed. Once grout is mixed, it is important to keep it agitated continuously prior to pumping. Although, this product has a long pot life, if the grout is allowed to sit then it will 'gel' and may become more difficult to pump.
- 3.3 Once the site is ready for grout placement, commence pumping. It is important to pump continuously and avoid the formation of cold joints.
- 3.4 Following completion, dispose of excess production material in consideration of the environment. Carefully wash out mixer tanks and agitators into the pump hopper and pump the resulting washout material through the grout hoses to a suitable disposal site. Drain any water out of the lines and hoses. Clean down the machinery and surrounding areas.

APPLICATION TEMPERATURES

- 4.1 As with the water temperature, the higher the air temperature the more quickly the grout hydrates and sets. Bluey Technologies specify mixing times and set times at an ambient temperature of 20°C. These times vary with temperature fluctuations, and adjustments will be required to compensate for this. Exposing the pumping hoses to the sun on a hot day accelerates the product's set time. In some cases it may be necessary to cool the material, the mix water, or even the hose itself during the process and pre-planning the storage of all materials to keep the temperature as low as possible.

APPLICATION

- 5.1 The product may be poured or pumped into place. Check formwork for leaks prior to mixing and application of grout. Do not exceed the maximum application thicknesses specified in this data sheet for any wet layer. Consult Bluey Technologies for further information about aggregate addition for large volume pours. BluCem SL50 does not require trowelling or finishing with air-release rollers. The product has been specially formulated to provide surface finish independent of manual intervention.

CURING

- 6.1 No special curing techniques are required but it is important to minimise air flow across the surface for at least 24 hours.



BluCem SL50

RAPID FLOOR SELF-LEVELLING CEMENTITIOUS GROUT

Product Data

Please refer to Important Notice on following page

Packaging	20kg bags
Water Addition	4.8 - 6.5 litres of water per 20kg bag
Yield	~13.5 litres per 20kg bag
Application Thickness	Minimum 0mm (feather edge) Maximum 40mm in one application
Pump Life	10 minutes @ 20°C

TESTED CHARACTERISTIC	STANDARD	RESULT
Compressive Strength	AS1479.2 Appendix A	20MPa @ 24 hours 45MPa @ 7 days 50MPa @ 28 days
Flexural Strength	AS1012.11	5MPa @ 28 days
Setting Time	AS1012.18	Initial set - 15 minutes @ 20°C Final set - 2 hours @ 20°C



BluCem SL50

RAPID FLOOR SELF-LEVELLING CEMENTITIOUS GROUT

Contact Bluey

BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia
Ph +61 7 3399 3635 Fax +61 7 3899 9822 brisbane@bluey.com.au

SYDNEY

Bluey Technologies Pty Ltd
Unit 3, 35 Higginbotham Road, Gladesville NSW 2111 Australia
Ph +61 2 9807 2207 sydney@bluey.com.au

MELBOURNE

Bluey Technologies Pty Ltd
PO Box 170, Tullamarine VIC 3043 Australia
Ph +61 3 9826 5570 melbourne@bluey.com.au

PERTH

Bluey Technologies Pty Ltd
Ph +61 402 372 308 perth@bluey.com.au

AUCKLAND

Bluey Technologies
Ph +64 21 102 4797 nz@bluey.com.au

www.bluey.com.au

BLUEY ASIA PACIFIC DISTRIBUTOR

QUICSEAL CONSTRUCTION CHEMICALS PTE LTD

No.7 Eunos Avenue 8A, Eunos Industrial Estate, (S)409460 Singapore
Ph +65 6742 4466 Fax +65 6741 4666

www.quicseal.com

IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd