



# BluRez 301

## EPOXY MORTAR



BluRez 301 is supplied as a two component, high strength, solvent free epoxy patching mortar.

### Uses

BluRez 301 is suitable for a variety of applications including the preparation of long lasting industrial flooring, general structural applications and concrete restoration.

### Advantages

- High mechanical properties
- Resistant to a wide range of industrial chemicals
- Bonds well to damp surfaces
- Non flammable
- Underwater applications

### Preparation

Concrete should be at least 28 days old. All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications. Host concrete must be roughened and aggregate exposed to ensure good bond. Grinding, high pressure water blasting or shot blasting of the surface is recommended for this purpose. All surfaces must be free of dust, oils and surface contaminants. This may require steam cleaning or high pressure water blasting if site conditions permit. Prime concrete surfaces using mixed BluRez 302LV at a rate of 8m<sup>2</sup>/litre. BluRez 301 must be applied wet-on-wet or when the surface is still tacky.

### Mixing

Use a slow speed (400 rpm) mechanical mixer and mix thoroughly. Add one part of BluRez 301 hardener to three parts of BluRez 301 compound. Mix until uniform.

### Application

Mechanically clean concrete and steelwork to remove loose, weak and contaminated surfaces and rust, scale, etc. Degrease steelwork if necessary. Remove dust and debris. Ensure surfaces are dry and prime with BluRez 302LV, working into surface. Allow to cure for 5 - 10 minutes before firmly applying BluRez 301. A smooth surface may be obtained with a trowel. BluRez 302LV may be applied to dry or slightly damp, but not wet surfaces. BluRez 301 may be used on wet surfaces but must thoroughly worked into the wet surface to obtain complete surface protection and adhesion. BluRez 301 should not be applied more than 20mm thick in one application on vehicle surfaces, to prevent slumping. In most cases, where concrete surface is rough, no primer is required.



# BluRez 301

## HIGH STRENGTH EPOXY RESIN

### Product Data

Please refer to Important Notice on following page

Packaging	3kg and 12kg set
Coverage	~1.85 - 1.95 kg/m <sup>2</sup> /mm thickness
Thickness per Application	1 - 20 mm
Appearance	Part A: White Paste Part B: Soft Black Paste
Density	Part A: 2.20 ± 0.06 Part B: 1.85 ± 0.06
Mixing Ratio by Weight	3 Part A : 1 Part B
Mixed Colour	Grey
Pot Life	45 ± 5 mins (100g @ 25 ± 3°C in paper cup)
Water Immersion	May be applied and cured underwater
Full Cure	7 ± 2 days at 25°C ± 3°C
Storage Life	12 months in original packaging

TESTED CHARACTERISTIC	STANDARD	RESULT
Compressive Strength	ASTM C579: 2001 (2012)	≥60N/mm <sup>2</sup> @ 7 days
Tensile Strength	ASTM C307: 2003 (2012)	>13.8N/mm <sup>2</sup>



# BluRez 301

## HIGH STRENGTH EPOXY RESIN

### Contact Bluey

#### BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd  
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia  
Ph +61 7 3399 3635 Fax +61 7 3899 9822 [brisbane@bluey.com.au](mailto:brisbane@bluey.com.au)

#### SYDNEY

Bluey Technologies Pty Ltd  
Unit 3, 35 Higginbotham Road, Gladesville NSW 2111 Australia  
Ph +61 2 9807 2207 [sydney@bluey.com.au](mailto:sydney@bluey.com.au)

#### MELBOURNE

Bluey Technologies Pty Ltd  
PO Box 170, Tullamarine VIC 3043 Australia  
Ph +61 3 9826 5570 [melbourne@bluey.com.au](mailto:melbourne@bluey.com.au)

#### PERTH

Bluey Technologies Pty Ltd  
Ph +61 402 372 308 [perth@bluey.com.au](mailto:perth@bluey.com.au)

#### AUCKLAND

Bluey Technologies  
Ph +64 21 102 4797 [nz@bluey.com.au](mailto:nz@bluey.com.au)

[www.bluey.com.au](http://www.bluey.com.au)

#### BLUEY ASIA PACIFIC DISTRIBUTOR

##### QUICSEAL CONSTRUCTION CHEMICALS PTE LTD

No.7 Eunos Avenue 8A, Eunos Industrial Estate, (S)409460 Singapore  
Ph +65 6742 4466 Fax +65 6741 4666

[www.quicseal.com](http://www.quicseal.com)

#### IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd