



BluRez Epoxy III

HIGH PENETRATION EPOXY RESIN



BluRez Epoxy III is a two component epoxy liquid which requires only mixing to form a low viscosity injection resin.

Uses

BluRez Epoxy III is used for structural injection and grouting repairs, general concrete repairs, as a primer for porous concrete or as a sealer for floor toppings.

Advantages

- Low viscosity aids penetration
- Excellent surface wetting
- Solventless
- Bonds well to damp and dry surfaces
- Fast hardening

Preparation

Evaluate joint or crack for injection. Drill holes either side of the crack, sloping towards the crack at an angle of approximately 45°, beginning at a distance of 120 - 150mm from the crack. Insert packer at a depth of approximately 100mm. If using surface mounted packers place them over the prepared crack using an approved epoxy paste. The spacing of the packers will vary depending on the crack.

Mixing

BluRez Epoxy III is supplied in precisely proportioned packaging ready for mixing. It is critical to the successful use of this product that part portions are not mixed. Add the two components together being sure to add the complete proportion of Part B to Part A. Mix together using a slow speed mixer (400rpm) for at least 3 minutes or until a uniform mixture is achieved.

Application

Commence from the widest part of the crack and proceed injecting outwards along the crack in each direction. Turn on pump and slowly increase pressure to a maximum of 10 - 15 bar. Stop pumping for every litre injected and allow 1 - 2 minutes for reaction. Start and stop injection until the packer will no longer accept material or if the specified pressure has been reached. Move to the next packer and repeat injection process. Continue injection until crack is full and has been adequately sealed. Monitor the effectiveness of the work and allow to settle for 2 - 3 days before returning to site and completing additional injection if required.





BluRez Epoxy III

HIGH PENETRATION EPOXY RESIN

Product Data

Please refer to Important Notice on following page

Packaging	2 litre and 20 litre kits
Ratio	1 part hardener : 3 parts compound
Yield	4 - 8m ² per litre (applied as primer) 20 lineal metres of 0.5mm x 100mm per litre (crack injection)
Viscosity	100mPa.s @ 25°C
Pot Life	30 minutes @ 25°C
Solids Content	100%
Compressive Modulus	1.4GPa
Elongation	3.0% (at break)
Bond Strength	2.7MPa (due to concrete failure)
Recommended Crack Width	≥0.2mm
Water Absorption	0.70%
Shelf Life	9 months

TESTED CHARACTERISTIC	STANDARD	RESULT
Tensile Strength	ISO 527	60MPa
Compressive Strength	ISO 604	105MPa
Flexural Yield Strength	ISO 178	95MPa



BluRez Epoxy III

HIGH PENETRATION EPOXY RESIN

Contact Bluey

BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia
Ph +61 7 3399 3635 brisbane@bluey.com.au

SYDNEY

Bluey Technologies Pty Ltd
Suite 609, 55 Miller Street, Pyrmont NSW 2009 Australia
Ph +61 2 9807 2207 sydney@bluey.com.au

MELBOURNE

Bluey Technologies Pty Ltd
Ph +61 407 242 990 melbourne@bluey.com.au

PERTH

Bluey Technologies Pty Ltd
Ph +61 407 242 990 perth@bluey.com.au

AUCKLAND

Bluey Technologies
Ph +61 407 242 990 nz@bluey.com.au

www.bluey.com.au

BLUEY ASIA PACIFIC DISTRIBUTOR

QUICSEAL CONSTRUCTION CHEMICALS PTE LTD

No.7 Eunos Avenue 8A, Eunos Industrial Estate, (S)409460 Singapore
Ph +65 6742 4466 Fax +65 6741 4666
www.quicseal.com

IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd