



BluCem ZeoGlass

RECYCLED INORGANIC POLYMER FOR STRUCTURAL SEWER LININGS



BluCem ZeoGlass is a one component cement powder which requires only the addition of water to form an acid resistant structural mortar.

BluCem ZeoGlass is a sprayable, high build product suitable for civil engineering applications. BluCem ZeoGlass incorporates specially graded recycled glass aggregates and advanced cement technology to form a cementitious mortar with low drying shrinkage, high alkalinity, excellent acid resistance and high strength.

Application Advantages

- Ultra high build in one pass
- Negligible rebound
- Fast application
- Minimal dust emission
- Easy to hand trowel

Lifecycle Advantages

- Uses >50% recycled raw materials
- Low drying shrinkage
- High acid resistance
- High compressive and bond strength
- High flexural strength

About the Product

BluCem ZeoGlass had been developed using a blend of carefully selected recycled glass aggregates combined with our cementitious material to form the basis of this very dense, high build inorganic polymer structural sewer mortar. The selected aggregates are custom graded by Blueey Technologies to create maximum interlocking during dry spraying to build depths of several hundred millimetres in one pass, creating a strong and highly resistant structural repair mortar. BluCem ZeoGlass is an economical high-performance product with high acid resistance and is suitable for structural repairs in sewers and waste water environment.

Application Solutions

- Concrete protection
- Concrete repair
- Structural repairs of beams
- Columns and slabs
- Structural sewer repairs
- Floor repair and topping
- Water treatment plants

Project Specification Clause

ACID RESISTANT SHOTCRETE - The concrete repair cementitious mortar used for this project shall be a one component cement powder which requires only the addition of water to form a recycled inorganic polymer mortar. It shall be a pre-blended product that has independent testing to validate the performance outlined in the technical data table on the following pages. BluCem ZeoGlass manufactured by Blueey Technologies or equivalent shall be accepted.

Project Examples

Sewer repair and lining, airport construction, bridge repair, building repairs, dam construction and repair, jetty construction and repair, concrete structures, rail construction, rail repairs and shutdowns, retaining walls, sea wall repair and maintenance, tunnel lining, tunnel rock support, wharf repair and construction.





BluCem ZeoGlass

RECYCLED INORGANIC POLYMER FOR STRUCTURAL SEWER LININGS

Application Specification

CONCRETE PREPARATION

- 1.1 All defective host substrate must be removed prior to application. Defective material includes cracked or structurally weakened surfaces and also chloride contaminated and carbonated concrete. A concrete corrosion expert must be consulted for critical projects or structural applications.
- 1.2 Host concrete must be roughened and aggregate exposed to ensure good bond. Removal of laitance is important to ensuring good bond. Shot-blasting, scarification, mechanical chipping or high pressure water blasting may be used to achieve a recommended minimum CSP3 surface finish. The correct balance between roughening the surface and not causing further micro-cracking and damage should be trialled and assessed.
- 1.3 All surfaces must be free of dust, oils and surface contaminants. This may require steam cleaning or high pressure water blasting.
- 1.4 A perimeter edge of at least 10mm depth must be provided around the area for application.
- 1.5 Priming using BluCem API0 is recommended. Priming by saturation of the surface using water prior to application is also acceptable. Priming with epoxy primers or other products which prevent vapour transmission is not recommended.

STEEL PREPARATION

- 2.1 Following removal of all defective concrete, any partially exposed reinforcing bars shall be fully exposed to a depth of 20mm behind the bar.
- 2.2 If the bar has lost more than 20% of its original diameter then it should be replaced and the Structural Engineer must be consulted.
- 2.3 Where the original reinforcement is retained it must be cleaned to a standard surface purity of Sa 2.5 for chloride contaminated concrete and Sa 2.0 for carbonated concrete. This is best achieved by wet blasting or abrasive blasting.
- 2.4 If chloride contamination is present then high pressure wet blasting is the only acceptable method of cleaning. Priming of reinforcement is generally not required.
- 2.5 If the steel will be exposed to the atmosphere for several days after cleaning then an acceptable form of priming would be to mix GP cement into a slurry using BluCem API0 and apply a cement rich coating to the steel surface.

MIXING

- 3.1 For wet applications, add BluCem ZeoGlass to potable water in a clean vessel using a high shear mechanical mixer for at least three minutes. Do not mix more material than can be placed in 30 minutes. Add enough water to achieve the desired consistency within the water ratio limits specified in this data sheet.
- 3.2 For dry applications, empty the dry powder directly into the hopper and adjust water and air at the nozzle for suitable consistency.

PUMPING

- 4.1 Special pumping and mixing equipment are required for BluCem ZeoGlass which can be applied by either wet or dry spraying. Various models of batch mixers and continuous mixers are available for use. It is important to match your application's specifics with the capabilities of the mixer and pump. Bluey Technologies are able to recommend the right mixer for your project.
- 4.2 For wet spraying applications rinse the mixer and charge the pump hopper with sufficient water to flush and cool the pump and all grout lines thoroughly. Check to ensure that all lines and hoses are clear and unobstructed. Once grout is mixed, it is important to keep it agitated continuously prior to pumping.
- 4.3 Following completion, dispose of excess production material in consideration of the environment. Carefully wash out machinery and surrounding areas.

APPLICATION TEMPERATURES

- 5.1 As with the water temperature, the higher the air temperature the more quickly the grout hydrates and sets. Bluey Technologies specify mixing times and set times at an ambient temperature of 20°C. These times vary with temperature fluctuations, and adjustments will be required to compensate for this. Exposing the pumping hoses to the sun on a hot day accelerates the product's set time.

CURING

- 6.1 It is recommended that the final surface finish layer is coated with curing compound or otherwise maintained wet for at least three days.



BluCem ZeoGlass

RECYCLED INORGANIC POLYMER FOR STRUCTURAL SEWER LININGS

Product Data

Please refer to Important Notice on following page

Packaging	20kg, 1000kg, 1200kg bags
Water Addition	2.0 - 3.0 litres per 20kg bag
Yield	9.4 litres per 20kg @ 11% water
Build Scope	Up to 300mm in one pass vertical; up to 150mm in one pass overhead
Workability Time	30 minutes @ 20°C
Maximum Particle Size	3.0mm

TESTED CHARACTERISTIC	STANDARD	RESULT
Compressive Strength	AS1478.2 Appendix A	2.2 litres water per 20kg 20MPa @ 24 hours 35MPa @ 7 days 40MPa @ 28 days
Residual Compressive Strength After 28 day Acid Bath		No strength loss
Chloride Ion Content	AS1012.20	0.01%
Drying Shrinkage	AS1012.13	330 μ strain @ 7 days 550 μ strain @ 28 days
Setting Time	BS EN 196:Pt 3:2005	Final set - 180 - 240 minutes
Fresh Wet Density	AS1012.5	2270kg/m ³



BluCem ZeoGlass

RECYCLED INORGANIC POLYMER FOR STRUCTURAL SEWER LININGS

Contact Bluey

BRISBANE (HEAD OFFICE)

Bluey Technologies Pty Ltd
Unit 8, 53 Metroplex Avenue, Murarrie Qld 4172 Australia
Ph +61 7 3399 3635 brisbane@bluey.com.au

SYDNEY

Bluey Technologies Pty Ltd
Suite 609, 55 Miller Street, Pyrmont NSW 2009 Australia
Ph +61 2 9807 2207 sydney@bluey.com.au

MELBOURNE

Bluey Technologies Pty Ltd
Ph +61 407 242 990 melbourne@bluey.com.au

PERTH

Bluey Technologies Pty Ltd
Ph +61 407 242 990 perth@bluey.com.au

AUCKLAND

Bluey Technologies
Ph +61 407 242 990 nz@bluey.com.au

www.bluey.com.au

BLUEY ASIA PACIFIC DISTRIBUTOR

QUICSEAL CONSTRUCTION CHEMICALS PTE LTD

No.7 Eunos Avenue 8A, Eunos Industrial Estate, (S)409460 Singapore
Ph +65 6742 4466 Fax +65 6741 4666

www.quicseal.com

IMPORTANT NOTICE

This Technical Data Sheet is provided for general information and instruction only. Bluey does not warrant that the information it contains is accurate, reliable or complete. Bluey does not warrant that the product (or any related services) will achieve any of the characteristics set out herein in any particular application in the field, nor that it will be suitable for any specific use or purpose. The properties and characteristics set out herein represent typical testing results under laboratory conditions only. Results of actual product implementation may vary. Site-specific and project-specific criteria will affect product performance, including without limitation: surfaces, materials or products used with the product or to which the product is applied; and weather, climatic or seasonal conditions. The user must take into account all such criteria relevant to the project concerned when considering any desired results, including by undertaking trial mixing and application under site conditions. Not all product parameters are batch tested as part of the manufacturing quality control process, and performance may vary between batches.

If Bluey gives any express written product warranty in relation to the product, that warranty is subject to the foregoing qualifications, despite anything to the contrary in any other document. All other representations, advice, suggestions or promises regarding the product's performance or its implementation, whether verbal or in writing, and whenever given, including in the course of any field services, are expressly disclaimed. Without limiting the foregoing, Bluey will have no liability for loss or damage of any kind if any application specifications are not followed.

The foregoing is not intended to exclude any warranties or guarantees which by law cannot be excluded. Subject only to the foregoing provisions of this Notice, and to the extent permitted by law, Bluey disclaims all liability for loss or damage of any kind suffered as a result of or in connection with the product or its implementation. If such liability cannot be wholly excluded, Bluey's liability will, to the extent permitted by law, be limited to the replacement of the product itself or the direct cost of replacement of the product itself (not including any collateral or consequential loss or damage of any kind).

© Bluey Technologies Pty Ltd