



# QUICSEAL 192

## CRYSTALITE

### Description

QUICSEAL 192 Crystalite is a chloride free chemical admixture supplied in the form of a grey powder and is added into concrete and mortars to impart self-sealing and waterproof properties.

When added into concrete, the active chemicals reacts with moisture in concrete and the by-products of cement hydration which generates a non-soluble crystalline formation throughout the pores and capillary tracts of the concrete.

These crystals formation fills all the pores and capillaries, resulting in a concrete impermeable to the migration of water or waterborne chemicals. During the curing stage, QUICSEAL 192 enhances the concrete's hydration process by forming massive hydration crystal growth.

QUICSEAL 192 waterproof concrete is unique in its ability to improve over time. The unreacted active ingredients will reactivate whenever the water seeps in, eventually blocking the capillary pores to prevent damage caused by water.

### Uses

QUICSEAL 192 is recommended for waterproofing and protection of:

- Raft foundations and retaining wall
- Basement walls and slab
- Ground slab and suspended slabs
- Water tanks, marine and other water containment structures
- Swimming pools, ponds, water features
- Tunnels and pipelines
- Shotcrete
- Precast

### Advantages

- Cost saving against waterproofing membranes, liners or coating
- Protects reinforcement steel from corrosion
- Reduces shrinkage and cracking
- Self-seals hairline cracks up to 0.4mm from subsequent shrinkage, settling or shifting
- Integral protection is maintained even if surface damage occurs, unlike surface applied films or coatings.
- Cured treatment within concrete becomes a permanent waterproof system, capable of withstanding high water pressure.
- Facilitates faster backfilling – saving time and money
- Economical – easy to apply and install compared to other systems
- Versatile usage – product can be used as an additive or applied by dry shake.

### Mix Design Guidelines

QUICSEAL 192 Crystalite is a dry powder admixture that is added to the concrete mix at the rate of 0.75% to 0.90% by weight of the cement content. Adjust the water content depending on slump requirement. Optimum dosage of QUICSEAL 192 to meet with requirements must be assessed throughout the trial mixes.

### Batching and Mixing

Add QUICSEAL 192 into the concrete mixer during batching. The correct quantity of QUICSEAL 192 should be measured and then added to the concrete during the mixing process either by hand or mechanical means. Mix the materials for a minimum of 5 minutes to ensure that QUICSEAL 192 has been thoroughly dispersed throughout the concrete.

### Joints

Adequate water-stops must be provided between movement and construction joints.

### Curing

As with all structural concrete, good curing practice should be maintained. Proper curing by using QUICSEAL 507 Cure-shield WB curing compound, spraying with water, wet hession or other means of preventing drying shrinkage and mass cracking.

## Packaging

- 20kg per bag

## Technical Data

PREPERTIES	TEST RESULTS
<b>Compressive strength</b> Based on G35 concrete mix BS EN 12390-3 : 2009	52.6 MPa (Control) 50.3 MPa (Treated with QUICSEAL192)
<b>Water Penetration Test</b> DIN 1048 : Pt 5 : 1911 Pressure applied 5kg/cm <sup>2</sup> Test Duration 72 hours	19.2mm @ 28 days (Control) 12.0mm @ 28 days (Treated with QUICSEAL192) 7.1mm @ 56 days (Treated with QUICSEAL192)
Coefficient of Permeability BTD/TP/02/2002 (HDB Cell Method)	4.43 X 10 <sup>-13</sup> m/sec

## Health & Safety

Gloves and goggles should be worn. Any contact to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, seek medical advice. Powder products should be handled to minimize dust formation. Use a light mask if excessive dusting is unavoidable.

## Important Notes

The information set forth herein is furnished in good faith and is based on technical data that QUICSEAL considers to be reliable. This information is intended for used by persons having technical skill and at their own discretion and risk. Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of QUICSEAL products as of the date of publication of this document. QUICSEAL makes no other warranties and assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact QUICSEAL.

Reference No. QS192/171121

QUICSEAL CONSTRUCTION CHEMICALS PTE LTD  
[www.quicseal.com](http://www.quicseal.com)

*QUICSEAL – the professional's choice of quality products and systems for building construction*