



SGBP 4836

# QUICSEAL 600

Tilebond

## Description

QUICSEAL 600 TILEBOND is a grey or white powder adhesive composed of cement, graded fine sand, synthetic resins and specially formulated additives to be mixed with water as a thin-set tile adhesive with very good adhesion strength.

When cured, QUICSEAL 600 is water resistant and has excellent thixotropic and shrinkage control properties.

## Classification:

EN 12004 : C1T

## Typical Uses

QUICSEAL 600 is suitable for bonding ceramic tiles, quarry tiles, klinker, mosaics, natural stones, etc.

- both wall and floor;
- internal and external areas;
- conventional cement-sand screeds and renders.

## Limitations

Do not use QUICSEAL 600 to:

- bond tiles on walls subjected to flexing and vibration (such as very thin plywood and gypsum board walls). Use QUICSEAL 605 MULTIPURPOSE PASTE or QUICSEAL 606 TILEFLEX;
- bond tiles on metal surfaces. Use QUICSEAL 612 TILEPOXY;
- bond moisture sensitive stones. QUICSEAL 612 TILEPOXY.
- Bond tiles on areas subjected to high movement or traffic (such as vehicular driveway)

## Substrate Preparation

The substrates must be levelled, clean and sound, free of dust and loose particles. Laitance, oil, grease, mould release agents or curing compound must be removed from concrete surfaces by using wire brush, scabblor or other means.

Extremely porous and powdery substrates (e.g. gypsum or prefabricated plaster panels, etc.) should be treated with QUICSEAL 113 PRIMER C before laying tiles with QUICSEAL 600 adhesive.

It is advisable to allow screeds and renders to cure for at least 7 days and surfaces which have become heated from exposure to direct sunlight should be dampened with water to prevent premature curing.

## Mixing Instructions

Pour approximately 6 litres of water into a clean container. Slowly add 25 kg of QUICSEAL 600 and mix with a slow speed mechanical mixer until homogenous and lump free paste is obtained. Allow the mix to stand for 5 minutes and re-stir before use.

## Technical Data

Product Type	Powder
Colour	Grey or White
Mixing Ratio	Approx. 6 ltrs of water : 25kg of QUICSEAL 600
Density of Mix	1.6 g/cm <sup>3</sup>
Pot Life	Approx. 2 hours
Application Temperature	+5 °C to +45 °C
Open Time	Approx. 15 - 20 minutes
Adjustability	Approx. 30 minutes
Ready for Light Traffic	24 hours
Service Temperature	-30 °C to 90 °C
Compressive Strength	
-7 day	19MPa
-28 day	35MPa

CLASSIFICATION	DESCRIPTION	EN 12004 REQUIREMENT	QUICSEAL 600
C1	Adhesion Strength -28 days' -Water immersion -Heat ageing	≥ 0.5 N/mm <sup>2</sup> ≥ 0.5 N/mm <sup>2</sup> ≥ 0.5 N/mm <sup>2</sup>	Passed Passed Passed
T	Slip	< 0.5mm	Passed

### **Application**

To achieve good adhesion, firstly apply a thin coat of QUICSEAL 600 adhesive firmly onto the substrate using the straight edge of the trowel followed immediately with the appropriate amount of adhesive with the notch side to achieve the required thickness. The correct notched trowel size to use will depend on the type and size of the tiles.

For large sized tiles and tiles with lugs and grooves, apply a coat of QUICSEAL 600 adhesive to the back of the tiles to ensure sufficient coverage when laid.

Lay the tiles onto the adhesive and ensure that a firm pressure is applied to achieve good contact with the adhesive.

Unfavourable climatic conditions such as strong sunlight, wind and high temperature, etc. and very porous substrates may reduce the open time of the adhesive. Hence, careful checks have to be made to ensure that skinning does not occur on the surface of the adhesive before laying the tiles. If a skinning has occurred, rework the adhesive before laying the tiles.

The tiles must be adjusted within 30 minutes after laying and must be protected from rain or strong sun for at least 24 hours.

Tile joints can be grouted usually 6 to 8 hours after laying the tiles

### **Cleaning**

All tools and hands may be cleaned with abundant water before the adhesive sets. After setting, cleaning becomes very difficult but can usually be helped by mechanical means.

### **Coverage**

1.6kg per m<sup>2</sup> per 1mm thick

The coverage is also affected by the condition of the substrate.

### **Packing**

QUICEAL 600 is supplied in 25 kg bags.

### **Storage**

12 months in a dry place in the original packaging

### **Important Notes**

The information set forth herein is furnished free of charge in good faith and is based on technical data that QUICSEAL considers to be reliable. This information is intended for used by persons having technical skill and at their own discretion and risk. Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of QUICSEAL products as of the date of publication of this document. QUICSEAL makes no other warranties and assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, please contact QUICSEAL.

Reference No. QS 600/060922

[ARDEX-QUICSEAL SINGAPORE PTE. LTD.](http://www.ardex-quicseal.com)  
[www.ardex-quicseal.com](http://www.ardex-quicseal.com)